




International Journal of Current Pharmaceutical & Clinical Research



www.ijcpcr.com

EVALUATION OF ANTIBACTERIAL EFFICACY OF SILVER NANO PARTICLES USING *POUTERIA CAMPECHIANA EXTRACT*

R.Kirubha* and G.Alagumuthu

P.G & Research centre, Department of chemistry, Sri Paramakalyani College, Manonmaniam Sundaranar University, Alwarkurichi-627 412, India.

ABSTRACT

Nanoparticles of interest in nanotechnology and medicine can be produced both by anorganic and organic synthesis. The biogenic production is now of high interest due to simplicity of the procedures and their versatility. The use of plants in the synthesis of nanoparticles emerges as an ecofriendly and existing approach. The nanoparticles were synthesized by using aqueous extract of *Pouteria campechiana* fruit. Synthesized nano particles were characterized using UV-visible spectrophotometer, X-ray diffractometer (XRD). High Resolution Transmission Electron Microscopy (HRTEM) and Cyclic voltammetry (CV). From XRD analysis, the average size of the silver nanoparticles was measured 44.4 nm. The synthesized nanoparticles are evaluated for its antimicrobial activity against human pathogens.

Key words: silver Nanoparticles, *Pouteria campechiana*, TEM, Antibacterial activity.

INTRODUCTION

Nanoparticles are being viewed as elementary building blocks of nanotechnology. The most important and distinct property of nanoparticles is that they show evidence of larger surface area to volume ratio. The most successfully studied nanoparticles today are those made from noble metals, in particular Ag, Pt, Au and Pd. Metal nanoparticles have marvelous applications in the area of catalysis, optoelectronics, diagnostic biological probes and display devices. [1]. Conventionally, nanomaterials are synthesized using either chemical or physical methods which include sol process, micelle, chemical precipitation, hydrothermal method, pyrolysis, and chemical vapour deposition [2]. Some of these methods are easy and provide control over crystallite size by restoring the reaction environment. But problem still exists with the general stability of the product and in achieving monodisperse nanosize using these methods [3]. Moreover, many of the conventional techniques have been found to be capital intensive and inefficient in materials and energy use [4].

alternative to the conventional methods for synthesis of NPs. Synthesis of inorganic nanoparticles by biological systems makes nanoparticles more biocompatible and environmentally benign [5]. Many plants such as Geranium leaf [6], Alfalfa [7], *Azadirachta indica* [8], *Lemon grass* [9], *Aloevera* [10], *Cinnamomum Camphora* [11], *Emblia officinalis* [12], *Capsicum annum* [13], *Diospyros kaki* [14], *Carica papaya* [15], *Coriandrum sp.* [16], *Boswellia ovalifoliolata* [17], *Tridax procumbens*, *Jatropha curcas*, *Solanum melongena*, *Datura metel*, *Citrus aurantium* [18], *Aegle marmelos* [19], *Cissus quadrangularis* [20] and *Morinda tinctoria* [21] have shown the potential of reducing nature for the formation of NPs.

The present study aims at the synthesis of silver nanoparticles from the aqueous extract of *Pouteria campechiana* fruits. We also attempt to combine the inherent antimicrobial activities of silver nanoparticles for enhanced antimicrobial activity.

Biological methods have emerged as an

Corresponding Author :- R.Kirubha Email:- rosekirubha@gmail.com

MATERIALS AND METHODS

Materials

Fresh plants of *Pouteria campechiana* were identified and collected from Tamilnadu Agricultural University, Tirunelveli, Tamilnadu, India and the taxonomic identification was made by Botanical Survey of India, Coimbatore. Silver nitrate was obtained from the precision scientific co, Coimbatore, India.

Synthesis of silver nanoparticles

The fresh plant of *Pouteria campechiana* broth solution was prepared by taking 120 g of thoroughly washed and finely cut plants in a 500 mL Erlenmeyer flask along with 250 mL of sterilized double distilled water and then boiling the mixture for 20 min before finally decanting it. The extract was filtered through Whatman filter paper no 1 and stored at -15°C and could be used within 1 week. The filtrate was treated with aqueous 1 mM AgNO_3 solution in an Erlenmeyer flask and incubated at room temperature. As a result, a dark brown coloured solution was formed; indicating the formation of silver nanoparticles and it was further confirmed by UV-Vis spectrum analysis [22]. It showed that aqueous silver ions could be reduced by aqueous extract of plant parts to generate extremely stable silver nano particles in water (Figure 1).

Characterization of the synthesized silver nanoparticles using UV-spectra

Synthesis of silver nanoparticles solution with plants extract may be easily observed by ultraviolet-visible (UV-Vis) spectroscopy. The bio-reduction of the Ag^+ ions in solutions was monitored by periodic sampling of aliquots (1 mL) of the aqueous component and measuring the UV-Vis spectra of the solution. UV-Vis spectra of these aliquots were monitored as a function of time of reaction on a Vasco 1301 spectrophotometer in 400-600 nm range operated at a resolution of 1 nm.

X-ray diffraction (XRD) analysis

The particle size and nature of the silver nanoparticle were determined using XRD. This was carried out using Shimadzu XRD-6000/6100 model with 30 kv, 30 mA with Cu $k\alpha$ radiations at 2θ angle. The analyzed material is finely ground, and average bulk composition is determined. The particle or grain size of the particles on the silver nanoparticles was determined using Debye Scherer's equation. $D = 0.94 \lambda / \beta \cos\theta$.

Transmission electron microscopy (TEM)

Transmission electron microscopy (TEM) (HITACHI, H-7500) is a microscopy technique whereby a beam of electrons is transmitted through an ultra-thin specimen, interacting with the specimen as it passes through. Ag nanoparticle image was formed from the

interaction of the electrons transmitted through the specimen; the image of Ag nanoparticles was magnified and focused onto an imaging device.

Cyclic Voltammetry analysis

Analysis through cyclic voltammetry (CV) confirmed the presence of elemental silver signal of silver nanoparticles. The change in the oxidation state of the metal ion was studied by CV technique, using platinum electrode with fresh surface at the rate of 25mVs^{-1} in the potential range between -1.0 and 1.0V.

Antimicrobial activity study

Antibacterial activities of the synthesized Ag nanoparticles were determined, using the agar disc diffusion assay method. Approximately 20 mL of molten and cooled Muller Hinton agar media was poured in sterilized petri plates. The plates were left overnight at room temperature to check for any contamination to appear. The test organisms were grown in selected broth for 24 h. 100 mL of broth culture of each test organism was used to prepare lawns. Agar of 5 mm diameter was prepared with the help of a sterilized stainless steel cork borer. Four plates were prepared in the agar plates. Ciprofloxacin was used as standard and positive controls. The plates containing the test organism and Ag nanoparticles were incubated at 37°C for 24 - 48 h. The plates were examined for evidence of zones of inhibition, which appear as a clear area around the plates. The diameter of such zones of inhibition was measured using a meter ruler and the mean value for each organism was recorded and expressed in millimeter.

RESULTS AND DISCUSSION

UV-VIS spectra analysis

The spectra were recorded after at 0, 2, 4, 6, 8 and 10 min. The effect of the reaction time on AgNPs synthesis was also evaluated with UV-Visible spectra and with time, the peak become sharper. The SPR band of silver nanoparticles appears at 437 nm and even after 10 min of incubation only slight variation was observed (fig 2). The increase in intensity could be due to increasing the number of nanoparticles formed as a result of the reduction of silver ions present in the aqueous solutions[23].

XRD studies

The XRD spectrum (Figure 3) has three distinct diffraction peaks at 37.2° , 46.4° and 63.9° , which are indexed (111), (200) and (220) of the face-centered-cubic (fcc) silver, respectively (figure .3). The obtained data was matched with the JCPDS file No.03- 0921 and the same results were also reported earlier [24]. The average grain size of the silver nanoparticles formed in the process was estimated from the Debye-Scherrer equation and the mean size of the particle was 44.4nm.

TEM analysis of Ag nanoparticles

The resulting silver nanoparticles was analysed with TEM techniques and conclude that the average mean size of Ag nanoparticles was 44.4nm, which seems to be spherical in morphology as shown in (Figure 4).

Cyclic Voltammetry analysis

In cyclic voltammetric analysis the *Pouteria campechiana* plant extract free solution makes all the metal ions are reduced to lower oxidation state, since there is no possibility for the formation of NPs. Upon addition of *Pouteria campechiana* extract in the reaction medium, the cathodic peak shifted towards the negative potential direction, implying that the reduced silver NPs are stabilized by *Pouteria campechiana* extract (Fig. 5). The extent of decrease in anodic peak current is greater than that of the cathodic peak current due to the fact that the rate of reduction of silver ion may be greater than its oxidation. This might be because of the electron donating methoxy, hydroxyl and amine groups containing *Pouteria campechiana* extract can provide a suitable environment for the formation of nanoparticles. The cyclic voltammogram of AgNPs shows the peaks observed at -0.27 and 0.21V.

It is assumed that only the oxidized form Ag^+ is present initially. Thus, a negative-going potential scan is chosen for the first halfcycle, starting from a value where no reduction occurred. As the applied potential approaches the redox process, a cathodic current begins to increase, until a peak is reached. The sweep is reversed after traversing the potential region where the reduction process takes place. During the reverse scan, Ag molecules are reoxidized back to Ag^+ and it result in an anodic peak.

Antibacterial Activity study

The antibacterial activity of silver nanoparticle

was tested against the following microorganism, viz; *E.Coli*, *Staphylococcus aureus*, *Bascillus cereus*, and *Pseudomonas aeruginosa* by disc diffusion method and the results were tabulated in the table 1. The silver nanoparticle has shown antibacterial activity against all tested microorganism and maximum zone of inhibition was found against *Pseudomonas aeruginosa*.(figure 6).

It is well known that Ag ions and Ag-based compounds have strong antimicrobial effects [25], and many investigators are interested in using other inorganic nanoparticles as antibacterial agents [26-28]. These inorganic nanoparticles have a distinct advantage over conventional chemical antimicrobial agents. The most important problem caused by the chemical antimicrobial agents is multidrug resistance. Generally, the antimicrobial mechanism of chemical agents depends on the specific binding with surface and metabolism of agents into the microorganism. Various microorganisms have evolved drug resistance over many generations. Thus far, these antimicrobial agents based on chemicals have been effective for therapy; however, they have been limited to use for medical devices and in prophylaxis in antimicrobial facilities. Therefore, an alternative way to overcome the drug resistance of various microorganisms is needed desperately, especially in medical devices, etc. Ag ions and Ag salts have been used for decades as antimicrobial agents in various fields because of their growth-inhibitory capacity against microorganisms. Also, many other researchers have tried to measure the activity of metal ions against microorganism [29, 30]. However, Ag ions or salts has only limited usefulness as an antimicrobial agent for several reasons, including the interfering effects of salts and the antimicrobial mechanism of the continuous release of enough concentration of Ag ion from the metalform. In contrast, these kinds of limitations can be overcome by the use of Ag nanoparticles.

Fig 1. Photographs showing A) pure $AgNO_3$ solution B) pure *Pouteria campechiana* plant Extract C) Colour changes after adding plant Extract with $AgNO_3$ solution




Fig 2. UV Spectra of silver nanoparticles




Fig 3. XRD of biosynthesized silver nanoparticles using the plant extract of *Pouteria campechiana*




Fig 4. HR-TEM image of silver nanoparticles using the plant extract of *Pouteria campechiana*




Fig 5. Cyclic voltammograms of silver nanoparticles




Fig 6. Antibacterial activity of silver Nanoparticles using *Pouteria campechiana* plant extract




Table. 1. Antibacterial activity of silver Nanoparticles

Microorganism	Zone of inhibition in mm			Ciprofloxacin
	20µl	40µl	60µl	
<i>E.Coli</i>	8.63±0.68	9.14±0.49	10.21±0.47	13.45±0.11
<i>Bacillus cereus</i>	8.55±0.56	9.54±0.45	10.25±0.79	14.56±1.01
<i>Staphylococcus aureus</i>	8.29±0.25	9.65±0.45	9.98±1.56	16.65±1.25
<i>Pseudomonas aeruginosa</i>	8.43±0.33	9.65±0.45	17.54±0.66	13.64±0.05

CONCLUSION

In this investigation, the biosynthesized silver nanoparticles were characterized by UV-Vis, HR-TEM, XRD and CV measurements. This green synthesis method is alternative to chemical method, since it is cheap, pollutant free and eco-friendly. The potential antimicrobial activity of silver nanoparticles was performed and the maximum antibacterial activity was observed against

Pseudomonas aeruginosa. Applications of such eco-friendly nanoparticles in bactericidal, wound healing and other medical and electronic applications, makes this method potentially exciting for the large-scale synthesis of other inorganic nanomaterials. Toxicity studies of silver nanoparticles on human pathogen open a door for a new range of antibacterial agents and anticancer agents.

REFERENCES

- Roy N and Barik A. Green synthesis of silver nanoparticles from the unexploited weed resources. *International Journal of Nanotechnology*, 4, 2010, 95.

2. Leela A and Vivekanandan M. Tapping the unexploited plant resources for the synthesis of silver nanoparticles. *African Journal of Biotechnology*, 7(17), 2008, 3162–3165.
3. Kowshik M *et al.*, Microbial synthesis of semiconductor CdS nanoparticles, their characterization, and their use in the fabrication of an ideal diode. *Biotechnology and Bioengineering*, 78(5), 2002, 583–588.
4. Klaus-Joerger T *et al.*, Bacteria as workers in the living factory: metal-accumulating bacteria and their potential for materials science. *Trends in Biotechnology*, 19(1), 2001, 15–20.
5. Govindaraju K *et al.*, Biogenic silver nanoparticles by *Solanum torvum* and their promising antimicrobial activity. *Journal of Biopesticides*, 3(1), 2010, 394–399.
6. Shankar SS *et al.*, Geranium leaf assisted biosynthesis of silver nanoparticles. *Biotechnology Progress.*, 19(6), 2003, 1627–1631.
7. Gardea-Torresdey JL *et al.*, Alfalfa sprouts: a natural source for the synthesis of silver nanoparticles. *Langmuir*, 19(4), 2003, 1357–1361.
8. Shankar SS *et al.*, Rapid synthesis of Au, Ag, and bimetallic Au core-Ag shell nanoparticles using Neem (*Azadirachta indica*) leaf broth. *Journal of Colloid and Interface Science*, 275(2), 2004, 496–502.
9. Shankar SS *et al.*, Controlling the optical properties of lemongrass extract synthesized gold nanotriangles and potential application in infrared-absorbing optical coatings. *Chemistry of Materials*, 17(3), 2005, 566–572.
10. Chandran SP *et al.*, Synthesis of gold nanotriangles and silver nanoparticles using Aloe vera plant extract. *Biotechnology Progress*, 22(2), 2006, 577–583.
11. Huang J *et al.*, Biosynthesis of silver and gold nanoparticles by novel sundried Cinnamomum camphora leaf. *Nanotechnology*, 18(10), 2007, 105104.
12. Ankamwar B *et al.*, Biosynthesis of gold and silver nanoparticles using Emblica officinalis fruit extract, their phase transfer and transmetallation in an organic solution. *Journal of Nanoscience and Nanotechnology*, 5(10), 2005, 1665–1671.
13. Li S *et al.*, Green synthesis of silver nanoparticles using Capsicum annum L. extract. *Green Chemistry*, 9(8), 2007, 852–858.
14. Song JY and Kim BS. Biological synthesis of bimetallic Au/Ag nanoparticles using Persimmon (*Diopyros kaki*) leaf extract. *Korean Journal of Chemical Engineering*, 25(4), 2008, 808–811.
15. Jain D *et al.*, Synthesis of plant-mediated silver nanoparticles using papaya fruit extract and evaluation of their anti microbial activities. *Digest Journal of Nanomaterials and Biostructures*, 4(3), 2009, 557–563.
16. Narayanan KB and Sakthivel N. Coriander leaf mediated biosynthesis of gold nanoparticles. *Materials Letters*, 62(30), 2008, 4588–4590.
17. Ankanna S *et al.*, Production of biogenic silver nanoparticles using Boswellia ovalifoliolata stem bark. *Digest Journal of Nanomaterials and Biostructures*, 5(2), 2010, 369–372.
18. Rajasekharreddy P *et al.*, Qualitative assessment of silver and gold nanoparticle synthesis in various plants: a photobiological approach. *Journal of Nanoparticle Research*, 12(5), 2010, 1711–1721.
19. Alagumuthu G and Kirubha R. Biofabrication and antibacterial activities of gold nanoparticles using *Aegle Marmelos* fruit extract. *Inter. J. Adv. Sci and Technol*, 6(6), 2013, 73-95.
20. Alagumuthu G and Kirubha R. Synthesis of gold phyto nanoparticles and their antibacterial efficacy. *International Journal of Chemical and Pharmaceutical Sciences*, 4(3), 2013.
21. Kirubha R and Alagumuthu G. *Morinda tinctoria* fruit assisted biosynthesis of silver nanoparticles. *Asian Journal of Pharmaceutical and Clinical Research*, 6(4), 2013, 60-64.
22. Mona S *et al.* Green Synthesis of Small Silver Nanoparticles Using Geraniol and Its Cytotoxicity against Fibrosarcoma. *Avicenna J Med Biotech*, 2, 2009, 111-115.
23. Vankar PS and Bajpai D. Preparation of gold nanoparticles from *Mirabilis jalapa* flowers. *Indian J Biochem Biophys*, 47, 2010, 157-160.
24. Isse JJ *et al.*, *Chem.Common.*, 2006, 344-346.
25. Enrique L, Roberto GVL and Ariel G. Gold nanoparticles as efficient antimicrobial agents for *Escherichia coli* and *Salmonella typhi*. *Chem.Central J*, 7, 2013, 11.
26. Garry G *et al.*, The cellular metabolism and Effects of gold complexes. *Metal. Based Drug*, 1, 1994, 395–404.
27. Hamouda J *et al.*, A novel surfactant nanoemulsion with a unique non-irritant topical antimicrobial activity against bacteria enveloped viruses and fungi. *Microbiol Res*, 156, 2000, 1 -7.
28. Fricker X. Medicinal chemistry and pharmacology of gold compounds. *Transit Met Chem.*, 21, 1996, 377–383.
29. Reddy GR *et al.*, Green synthesis characterization and in-vitro antibacterial activity of polyshaped gold nanoparticles by using sennasiamea (lam.) Plant leaf extract. *Int J Green Chem Bioproses*, 2(1), 2012, 1-5.
30. Speranza G *et al.*, Role of chemical interactions in bacterial adhesion to polymer surfaces. *Biomaterials*, 25(11), 2004, 2029-2037.